

weber ESL C25/30-4 Mortar for concrete element joints



- Both vertical and horizontal surfaces
- Plastic fibre-reinforced
- A domestic product certified with the FI mark under the supervision of Eurofins Expert Services Oy
- Certified EPD environmental product description
- The product is a declared item in the Supply Chain Declaration Portal (SCDP) for New Buildings generation 4.

ABOUT THIS PRODUCT

Non-sagging mortar especially designed for vertical and horizontal joints of concrete elements according to EN 1504-4, applied using a pump. Strength class C25/30-4 according to SFS-EN 206. Maximum grain size 4 mm.

AREA OF USE

Principally designed for the vertical and horizontal joints of concrete elements. In addition, it is suitable for casting the top and bottom joints of wall elements, for example, and for filling cracks and other holes and grooves without a need to use moulds. The product is certified as special mortar according to guidelines given by The Concrete Association of Finland (BY).

Product fulfills the requirements according to SFS-EN 1504-4 (part 4: Structural bonding), product intended for structural bonding as cementitious mortar for jointing of concrete elements both vertically and horizontally according principle 4.4.

PRODUCT SPECIFICATION

Recommended water content	13-14 l/100 kg of dry mix (13-14%)
Mixed volume	Approx. 470 l/1000 kg
Pot life (Operating time)	Approx. 30 minutes
Binder	Cement
Aggregate	Natural sand, grain size 0-4 mm
Additive	Additives that improve workability and weather resistance, and compensate for shrinkage
Adhesion strength 28 days	> 4.0 MPa (Flexural bond strength, EN 12636). > 15 MPa (Slant shear strength, EN 12615).
Compressive strength class	C25/30-4 when pumped.
Compressive strength 1 day	Approx. 15 MPa (EN 12190)
Compressive strength 7 days	Approx. 30 MPa (EN 12190)
Compressive strength 28 days	Approx. 40 MPa (EN 12190). > 30 MPa (Compressive strength to cube, EN 12390-3).
Unrestrained shrinkage 28 days	0.7 mm/m (EN 12617-4)
Fire class	A1 (EN 13501-1)
Exposure class	For applications in structures subject to exposure class requirements, refer to the separate Weber concrete products – classifications and approvals table available on the product page.
Modulus of elasticity	> 20 GPa (EN 13412)
Air content	4-9%
Chloride content	< 0.05% (SFS-EN 1015-17)
Density	Approx. 2100 kg/m ³
Water cement ratio	0.5 (with maximum water volume)
Equipment recommendations	Weber Pump Set, Stator Ü356-0,75. Steel reinforced minimum of 1.5" hose, for vertical use maximum of 40 m and horizontal casts maximum of 60 m.
Storage conditions	Shelf life is 12 months from date of manufacture (unopened package, dry space)
Package	25 kg sack. 1000 kg large sack.
GTIN-codes	6415910056810 (25 kg) 6415910056827 (1000 kg)
Certifications	CE, EPD, FI, Key Flag Symbol

SUBSTRATE

The joint must be clean, absorbent and preferably roughened. The width of the joint must be at least 15 mm. Use a stopper board if necessary.

MIXING

The mortar can be mixed with a screw mixer, for example. The mortar for concrete element joints is shovelled from the large sack into the mixer. Instead of the large sack, small sacks can also be used. During the mixing, max. 13-14% of water is added to the mortar.

WORK INSTRUCTIONS

After mixing, the mortar is pumped into the joint and levelled with a steel trowel. Do not vibrate the mortar for concrete element joints. If the water content is correct, the mortar will not sag out of the joint. If the joint is open on both sides, place a stopper board on one side of the joint. Remove the stopper board once a sufficient amount of time has elapsed (depending on the temperature, relative humidity and other factors affecting the setting time), and use a trowel to finish the joint. Pump the mortar into the joint carefully to ensure a compact and structurally functional joint.

AFTER-TREATMENT

The finished joints are kept moist for 2-3 days.

DISCLAIMER

As there are different conditions at every opportunity, Weber can not be held responsible for anything other than the information provided under the heading "Product Specification". Examples of information and circumstances, which are outside Saint-Gobain (whether specifically stated or not) include storage, construction, processing, interoperability with other products, workmanship and local conditions.