

weber JB 600/3 Non-shrink grout SR C50/60-4



- Easy flowing compound that fills the mould well
- Rapid strength development
- Resistant to salt and freezing
- Long adjustable time
- Withstands chemical stress even in exposure class XA3

ABOUT THIS PRODUCT

Salt and frost resistant, class R4 rapidly strengthening compound the volume of which expands slightly prior to setting. Strength class C50/60-4 according to SFS-EN 206. Maximum grain size 4 mm.

AREA OF USE

- Installation, pointing and second stage concrete application of concrete elements
- Anchorage soldering
- Difficult second stage and filler concrete applications in small spaces

Product fulfills the requirements of R4-class according to SFS-EN 1504-3, cementitious non-shrink grout to be used in accordance with concrete repair principles 3.2 or 4.4.

SUBSTRATE

The substrate concrete is cleaned carefully of impurities. The best adhesion is achieved on coarse or coarsened concrete. The substrate must be moistened with clean water prior to casting. The moistening must be commenced well in advance so that moisture will no longer be absorbed from the Non-Shrink Grout to the base concrete when casting. Any water that has not been absorbed into

PRODUCT SPECIFICATION

| | |
|--------------------------------|---|
| Recommended water content | 10-11% (2.5-2.75 l/25 kg of dry mix) |
| Mixed volume | Approx. 11-12 l/25 kg (Approx. 440-480 l/1000 kg) |
| Application temperature | The ambient temperature must remain above +5 °C. The optimum temperature of the compound is +10...+20 °C. The cast must not be allowed to freeze during the first 2 days after application. |
| Adjustable time | Approx. 30 minutes. |
| Binder | SR Cement |
| Aggregate | Natural sand, grain size 0-4 mm |
| Additive | Additives that improve workability and weather resistance and increase the volume of fresh concrete |
| Adhesion strength 28 days | > 2.0 MPa (EN 1542) |
| Compressive strength class | C50/60-4 |
| Compressive strength 1 day | Approx. 45 MPa (+20 °C, EN 12190) |
| Compressive strength 7 days | Approx. 60 MPa (+20 °C, EN 12190) |
| Compressive strength 28 days | Approx. 70 MPa (+20 °C, EN 12190) |
| Restrained shrinkage/expansion | Adhesion strength after test > 2.0 MPa (EN 12617-4) |
| Unrestrained shrinkage 28 days | 0.7 mm/m (EN 12617-4) |
| Fire class | A1 (EN 13501-1) |
| Exposure class | For applications in structures subject to exposure class requirements, refer to the separate Weber concrete products – classifications and approvals table available on the product page. |
| Frost resistance | XF4 (Salt-frost resistant) (Tile test SS-137244 Metod A and EN 13687-1) |
| Carbonation resistance | Pass (EN 13295) |
| Modulus of elasticity | > 20 GPa (EN 13412) |
| Air content | 2-5% (SFS-EN 1015-7) |
| Chloride content | < 0.05% (SFS-EN 1015-17) |
| Capillary absorption | ≤ 0.5 kg/(m ² ·h ^{0.5}) (SFS-EN 13057) |
| Expansion (early age) | Approx. +1% |
| Water cement ratio | 0.3 (with maximum water volume) |
| Volume weight wet | Approx. 2200 kg/m ³ |
| Equipment recommendations | Weber Pump Set with large sack silo or to normal sacks. Stator 50/7R or Betonstar, steel reinforced hose maximum of 60 m. |
| Storage conditions | Shelf life is 12 months from date of manufacture (unopened package, dry space) |
| Package | 25 kg sack, 1000 kg large sack. |
| GTIN-codes | 6415910049164 (25 kg) 6415910049140 (1000 kg) |
| Certifications | CE, Key Flag Symbol |

the substrate must be carefully removed prior to casting using a brush or pressurised air, for example. The cast must be applied from one side only. The mould of this side must be built higher and wider than the rest so that

the concrete will flow into the mould on its own weight (head box). Since Non-Shrink Grout is very easy flowing, the mould must be tight. When using galvanised steel in grouting or anchorage casting it must be ensured that the surface treatment has become passive. Non-passivated zinc reacts with the fresh concrete compound, resulting in the formation of hydrogen. The layer of hydrogen gas, which is formed around the steel, may cause the adhesion between the steel and the hardened concrete to break. The passivation of galvanised steel takes 2-3 weeks in a temperature of +15...+20 °C and 5-6 weeks in a temperature of 0...+5 °C. In unclear circumstances sufficient passivation must be ensured through preliminary testing. Passivity can also be achieved through chromate treatment.

MIXING

A total of 2.5-2.75 litres of clean potable water is added to one sack (25 kg) of Non-Shrink Grout, depending on the flexibility requirement. Mixing should ideally be carried out using a concrete mixer or a slowly rotating drilling machine beater. The minimum amount of water is measured into the mixing vessel and the dry product is added while stirring constantly. After the initial mixing the agility of the compound is inspected and if necessary, the remainder of the water is added. The maximum amount of water must not be exceeded. The temperature of the water should preferably be between +10...+30 °C. The temperature of the water is selected so that the temperature of the ready-to-use compound is +10...+20 °C. The mixing time when using mechanical mixing devices is 3-5 minutes.

WORK INSTRUCTIONS

Once mixed, Non-Shrink Grout remains suitable for casting for about 30 minutes. However, in order to fully benefit from the expansion, which affects the filling capacity of the grout, casting should be carried out as soon as possible after mixing. The casting is performed from one side only. If necessary, the pouring of the grout can be aided by compacting or gentle vibrating. The application temperature must remain above +5 °C. Fresh cast must not be allowed to freeze within the first two days after application.

If casts that exceed 100 mm in thickness are produced as a single layer, a compound of maximum stiffness must be used in order to avoid the risk of disintegration. However,

the following method should be preferred:

- Casting is carried out in two layers so that the layers are a maximum of 10 cm in thickness. The top layer is cast approximately 24 hours after the bottom layer.

Separate anchoring boltholes for machines and through holes in walls and floors can be done in one cast if material consumption in cast is less than 500 litres. More detailed working instructions are available in brochure "4-62 weber Juotoslaastit - Työohje", which is available in Finnish language.

AFTER-TREATMENT

Aftercare begins as soon as the casting has been completed, by protecting the surface from drying too quickly (moisture and cover). Gentle moistening can usually be commenced as soon as 30 minutes after the casting, once a more compact, soft cover layer has formed on the surface. Moistening ensures the sufficient expansion of the grout and a high level of hydration of the cement. Generous moistening must be continued for at least the duration of the first two days. Aftercare is then continued by spraying water on the surface and covering it, for example, or by using aftercare products for at least 7 days.

PLEASE OBSERVE

Notes on dimensioning:

The diameter of the hole for the anchor bolt must be at least 20 mm larger than the diameter of the bolt when measured at the thickest part of the anchor bolt/steel in. With large anchoring lengths, such as when anchoring into a rock, where it is difficult to ensure that the sides of the anchorage hole are straight and the hole free of impurities, the space between the bolt/steel and the hole may have to be larger than above.

DISCLAIMER

As there are different conditions at every opportunity, Weber can not be held responsible for anything other than the information provided under the heading "Product Specification". Examples of information and circumstances, which are outside Saint-Gobain (whether specifically stated or not) include storage, construction, processing, interoperability with other products, workmanship and local conditions.