

# weber 201 Final Coat Scratch



- Choose your favourite colour
- A durable product that ages beautifully
- The same product sprayed and rubbed, 201, Scratch
- The product is a declared item in the Supply Chain Declaration Portal (SCDP) for New Buildings generation 4.

## ABOUT THIS PRODUCT

Sprayed coloured lime cement plaster for coating lime cement rendering. The Final Coat mixture ratio is LC 50/50/600. The Final Coat contains mica to give the coating sheen.

## AREA OF USE

Suitable for coloured coating of lime cement rendering.

## SUBSTRATE

Suitable rendering substrates are weber lime cement rendering plasters. The filling plaster layer must be at least 2-3 days old and sufficiently hardened. The filling render surface should be coarse to provide sufficient adhesion for the Final Coat. When repairing old render surfaces, materials which weaken adhesion such as salts, laitance, dust, old organic paint and rust must be removed by, for example, wet sandblasting. If necessary, the substrate can be repaired using weber lime cement plasters.

## MIXING

One sack (20 kg) of 201 Final Coat is mixed in approx. 4.5 litres of clean water. Mixing time is 3-10 minutes depending on the power of the mixer. Open time is approx. 1-2 h

## PRODUCT SPECIFICATION

|                             |                                                                                                 |
|-----------------------------|-------------------------------------------------------------------------------------------------|
| Material consumption        | 3-5 kg/m <sup>2</sup> (rubbed surface).<br>4-6 kg/m <sup>2</sup> (roughcast surface).           |
| Recommended water content   | approx. 4.5 l/20 kg                                                                             |
| Binder                      | Slaked lime and cement                                                                          |
| Aggregate                   | Crushed limestone, grain size 0-1.5 mm                                                          |
| Additive                    | Inorganic pigments                                                                              |
| Fire class                  | A1, Non-combustible (EN 13501-1)                                                                |
| Water vapour permeability   | $S_d = 0.1$ (SFS-EN 1015-19)                                                                    |
| Water absorption            | < 1.2 kg/(m <sup>2</sup> min <sup>0.5</sup> ) (SFS-EN 1015-18)                                  |
| Painting product group 2012 | 422 Lime-cement coatings RL 11...13                                                             |
| Gloss level                 | Matte                                                                                           |
| Equipment recommendations   | Weber Pump Set to small sacks. Stators Superstar 0.5 or 50/7R, steel reinforced hose max. 50 m. |
| Color                       | Serpo colour map, 36 shades                                                                     |
| Storage conditions          | Shelf life is approx. 12 months from the date of manufacture (unopened package, dry space).     |
| Package                     | 20 kg sack                                                                                      |
| GTIN-codes                  | 6415910010744 (White T001)<br>6415910012007 (Serpo colours)<br>6415910012021 (Custom colours)   |
| Certifications              | CE, Key Flag Symbol                                                                             |

after adding water; in warm conditions the open time may be shorter. For colour uniformity, pliancy and mixing time of the mass must be the same from one mixing batch to another!

## WORK INSTRUCTIONS

Before starting the work, check that you have the correct product. A test patch must be made to make sure you have the desired colour shade and pattern! When coating, the substrate must be water absorbent. Do not apply Final Coat on wet or frozen substrates. After rain, wait for the substrate to recover absorbency and the moisture to even out. Moisture fluctuations on the substrate may cause the surface to be patchy. When plastering and at least 3 days thereafter, the substrate and surface temperature must be at least +5 °C. The recommended weather is cloudy with a temperature of +10...+20 °C. Surface coating in direct sunlight or strong winds should be avoided. Prior to coating, wood, glass and metal surfaces should be protected. The water flowing from the roof and from above the protruding parts of the facade must be redirected away from the rendering surface during and after work. Already in the planning phase it is important to note that rainwater should be directed in a controlled

manner away from the façades and windows. Continuous water leakage results in unsightly marks and causes deterioration in materials and premature damage. Final Coat is applied using a plastering pump or a funnel top sprayer. To avoid visible joints, wall surfaces should be divided into smaller sections that are always coated without a break. Work seams are placed at the least visible locations, such as, for example, at the expansion joints or behind drainpipes. Achieving a level surface requires a lift or scaffolding that provide good mobility and are far enough from the wall surface.

### Roughcast finish:

When spraying the roughcast finish, the spraying is done at least 2 times. The colour of the finished surface is influenced by, for example, the absorbency of the substrate, the consistency of the mass, the surface pattern and roughness, and the nozzle size and air volume of the spray gun. The first plaster layer is made with a more pliable plaster and sprayed with higher air pressure. The second coating can be done earliest the next day on a properly hardened surface. Various surface patterns are obtained by changing the plasticity of the mass, the nozzle size, the amount of spraying air and the spraying distance. More pliable plaster, high air volume and small nozzle give a smaller surface texture. The spraying distance with the spray gun is approx. 1 m and 0.6 m with a funnel top sprayer. Spraying from too close or using too pliable plaster causes the surface to become uneven and will easily result in shiny patches. The spraying must be perpendicular to the surface in rotating movements.

### Rubbed surface:

The coating can be sprayed or applied by hand with a trowel. The plaster surface is levelled to the maximum grain size layer thickness. A sharp-edged plastic float can be used for rubbing. The working method or type of float should not be altered during work and rubbing must be carried out continuously in one area without interruption.

### AFTER-TREATMENT

The surface must be protected from direct sunlight and kept damp for at least 3 days after coating. When the air is dry and warm, the rendered surface should be sprayed after coating.

### COATING

If necessary, the Final Coat surface can be painted with weber Silicate Paint or re-coated with weber Final Coat. Clean with water wash before re-coating.

### PLEASE OBSERVE

The mineral coatings for lime and cement bonds are characterized by the formation of a light-coloured lime and salt efflorescence on the plaster surface when the materials dry or, in the event of rain on a fresh rendered surface. Efflorescence occurs quite soon after the plastering work and, due to rain, it partially disappears over time. The phenomenon does not weaken the strength and durability of the coating. This phenomenon is particularly emphasized in dark shades, and it is therefore advisable to choose light shades for façade coatings where the visibility of efflorescence is low. If an especially even shade (especially dark colors) is desired for the rendered surface, the mineral coating must be painted using weber Silicate Paint.

### DISCLAIMER

As there are different conditions at every opportunity, Weber can not be held responsible for anything other than the information provided under the heading "Product Specification". Examples of information and circumstances, which are outside Saint-Gobain (whether specifically stated or not) include storage, construction, processing, interoperability with other products, workmanship and local conditions.

### SALES UNITS

| Product Code | GTIN          | Name                                     | Length | Width  | Height | Weight | SU/UoP2 | SU/UoP3 |
|--------------|---------------|------------------------------------------|--------|--------|--------|--------|---------|---------|
| 1009902      | 6415910012007 | weber 201 Jalolaasti hierto Serpo 20 kg  | 579 mm | 278 mm | 94 mm  | 20 kg  | 48      |         |
| 1009903      | 6415910012021 | weber 201 Jalolaasti hierto til.v. 20 kg | 579 mm | 278 mm | 94 mm  | 20 kg  | 48      |         |
| 1009901      | 6415910010744 | weber 201 T001 20 kg                     | 579 mm | 278 mm | 94 mm  | 20 kg  | 48      |         |