

weber RB 50/5 K Shotcrete with fibres



- Strength 50-60 MN/m²
- Fiber reinforced with plastic fibres
- Approved in the bridge repair instructions (SILKO) of the Finnish Road Authority

ABOUT THIS PRODUCT

Salt and frost resistant, class R4 shotcrete for structural repair of concrete. It is specially designed to be applied by dry mix process. Maximum grain size 5 mm. Also available with smaller grain size (RB 50/3 K) or without fibres (RB 50/5). On order also with sulphate resistant SR-cement (RB 50/5 K SR).

AREA OF USE

Product intended for structural repair of concrete as cementitious shotcrete mortar for concrete repair according principles 3.3. or 7.1. Product fullfills the requirements of R4-class according to SFS-EN 1504-3. It is suitable for bridge repair, reinforcement of foundations, application areas where formwork is difficult like tunnels, repair of damaged concrete, increasing of protective concrete layer for reinforcement steel and for concrete structures with special shapes.

SUBSTRATE

Concrete substrate is cleaned and coarsened carefully. Damaged concrete should be removed by high pressure water blasting. Reinforcing steel where exposed should be cleaned by abrasive action to bright metal and if necessary, protected with weber REP 05 Slurry Primer, see separate product datasheet. If necessary, the substrate

PRODUCT SPECIFICATION

Material consumption	Approx. 30 kg/m ² /10 mm layer, including approx. 30% waste.
Mixed volume	Approx. 480 l/1000 kg
Binder	Cement
Aggregate	Natural sand 0-5 mm
Additive	Plastic fibres
Adhesion strength 28 days	> 2.0 MPa (EN 1542)
Compressive strength 28 days	Approx. 50-60 MPa (EN 12390-3)
Restrained shrinkage/expansion	Adhesion strength after test > 2.0 MPa (EN 12617-4)
Fire class	A1 (EN 13501-1)
Exposure class	For applications in structures subject to exposure class requirements, refer to the separate Weber concrete products - classifications and approvals table available on the product page.
Frost resistance	Salt-frost resistant (EN 13687-1)
Carbonation resistance	Pass (EN 13295)
Chloride content	< 0.05% (SFS-EN 1015-17)
Equipment recommendations	Weber Mortar Station
Storage conditions	Shelf life is 12 months from the date of production (unopened package, in dry conditions)
Package	1000 kg large sack. Bulk in a silo.
GTIN-codes	6415990350419 (1000 kg) 6415990350433 (Bulk)
Certifications	CE, Key Flag Symbol

is moistened the day before application and lightly again just before the work is started. The substrate must be damp when application of shotcrete is started.

MIXING

RB 50/5 K Shotcrete is mixed with water. To prevent dusting and to ensure consistent quality of the sprayed layer it is recommended to pre-wet the mortar before application. Recommended moisture content after pre-wetting is about 6 weight-%. Pre-wetting can easily be done with Weber's silo-mixing equipment.

WORK INSTRUCTIONS

Application is done according to BY 41: BETONIRAKEN-TEIDEN KORJAUSOHJEET 2007 and Silko-manual by Finnish Road Authority. The temperature of substrate and air must be over +5 °C. The surface of the shotcrete can be left as sprayed structure, evened along level lining or scratched. Level lining must be removed and cavities filled before floating to prevent colour differences of final sur-

face. Scratched surface corresponds to surface defined in InfraRYL 42020.3.8.4. Due to that, it is not necessary to spray surface with more finer surface layer afterwards. The surface structure can be assured with a preliminary test.

AFTER-TREATMENT

The concrete is wetted and evaporation is prevented, using a plastic cover for at least 7 days. After-treatment should be started immediately after application by protecting the fresh surface from sunlight and wind. After-treatment can also be done by using suitable

aftercare products. If necessary the working area should be weather-protected to minimise the affect of climate variations.

DISCLAIMER

As there are different conditions at every opportunity, Weber can not be held responsible for anything other than the information provided under the heading "Product Specification". Examples of information and circumstances, which are outside Saint-Gobain (whether specifically stated or not) include storage, construction, processing, interoperability with other products, workmanship and local conditions.

SALES UNITS

Product Code	GTIN	Name	Length	Width	Height	Weight	SU/ UoP2	SU/ UoP3
1004060	6415990350419	weber RB 50/5 K 1000 kg	800 mm	800 mm	1000 mm	1000 kg		
1009155	6415990350419	weber RB 50/5 K 1000 kg	900 mm	880 mm	820 mm	1000 kg		
1004061	6415990350433	weber RB 50/5 K Ruiskubetoni Loose				1000 kg		