

weber RL 45 Sprayed Mortar SR C35/45-4



- Cement based and plastic fibre-reinforced
- Resistant to salt and freezing
- Can be sprayed with very low loss of material
- Withstands chemical stress even in exposure class XA3

ABOUT THIS PRODUCT

Salt and frost resistant, class R4 sprayed repair mortar, which is designed for structural repair of concrete by spraying. Strength class C35/45-4 according to SFS-EN 206. Maximum grain size 4 mm.

AREA OF USE

Product intended for structural repair of concrete as cementitious mortar for concrete repair according principles 3.3., 4.4 or 7.1. Product fulfills the requirements of R4-class according to SFS-EN 1504-3.

- Repairs of chemical stressed concrete water tanks by spraying
- Increasing of structural strength in bearing structures, such as beams
- Repair and tightening of old shotcrete surfaces
- Vertical joints of concrete elements
- Jointing of natural stone walls

SUBSTRATE

Damaged concrete should be removed by high pressure water blasting, for example. Surfaces that will be in contact with the mortar must be absorbent and free of dust, cement glue and other impurities that might weaken

PRODUCT SPECIFICATION

Material consumption	Approx. 20 kg/m ² /10 mm
Recommended layer thickness	Approx. 10-30 mm (at a time)
Recommended water content	3.25-3.75 l/25 kg
Mixed volume	Approx. 12-13 l/25 kg (Approx. 500 l/1000 kg)
Pot life (Operating time)	Approx. 1 h
Binder	SR Cement
Aggregate	Natural sand 0-4 mm
Additive	Additives that improve workability and weather resistance. Plastic fibres.
Adhesion strength 28 days	> 2.0 MPa (EN 1542)
Compressive strength 1 day	Approx. 10 MPa when sprayed (EN 12190)
Compressive strength 7 days	Approx. 40 MPa when sprayed (EN 12190)
Compressive strength 28 days	> 45 MPa when sprayed (EN 12190)
Restrained shrinkage/expansion	Adhesion strength after test > 2.0 MPa (EN 12617-4)
Fire class	A1 (EN 13501-1)
Exposure class	For applications in structures subject to exposure class requirements, refer to the separate Weber concrete products - classifications and approvals table available on the product page.
Frost resistance	Salt-frost resistant (EN 13687-1)
Carbonation resistance	Pass (EN 13295)
Air content	3-6%
Chloride content	< 0.05% (SFS-EN 1015-17)
Capillary absorption	≤ 0.5 kg/(m ² ·h ^{0.5}) (SFS-EN 13057)
Density	Approx. 2000 kg/m ³
Water cement ratio	0.45 (with maximum water volume)
Equipment recommendations	Weber Pump Set for coarse plasters and mortars, max. grain size 8 mm, with large sack silo or to normal sacks. Stator Ü356, steel reinforced hose maximum of 60 m.
Storage conditions	Shelf life is 12 months from the date of manufacture (unopened package, dry space)
Package	25 kg sack. 1000 kg large sack.
GTIN-codes	6415910049157 (25 kg) 6415910049119 (1000 kg)
Certifications	CE, Key Flag Symbol

the adhesion. The substrate is moistened before the work is started. The surface must be damp when spraying is started.

MIXING

The mortar can be mixed with a continuous screw mixer attached to a silo or mortar pump. The mortar can also be mixed with a pan mixer.

WORK INSTRUCTIONS

The temperature of substrate and air must be over +5 °C. Application is done according to normal working methods with wet sprayed mortars (please refer to BY 41: BETONIRAKENTEIDEN KORJAUSOHJEET 2007). The layer thickness on large surfaces is approximately 30 mm at a time. Individual holes up to 100 mm can be filled with single spraying. If needed, the surface is evened immediately and after drying a little while scratched with a wooden grinder. If spraying is done in more than one layer, lower layer is only evened, not scratched! Next layer can be sprayed normally the next day.

AFTER-TREATMENT

The mortar is wetted and evaporation is prevented, using for example a plastic cover for at least 7 days. The temperature of air must be over +5 °C during the after-treatment period.

DISCLAIMER

As there are different conditions at every opportunity, Weber can not be held responsible for anything other than the information provided under the heading "Product Specification". Examples of information and circumstances, which are outside Saint-Gobain (whether specifically stated or not) include storage, construction, processing, interoperability with other products, workmanship and local conditions.

SALES UNITS

Product Code	GTIN	Name	Length	Width	Height	Weight	SU/ UoP2	SU/ UoP3
1022090	6415910049157	weber RL 45 Ruiskulaasti SR 25 kg	490 mm	296 mm	124 mm	25 kg	40	
1022086	6415910049119	weber RL 45 Ruiskulaasti SR 1000 kg OJA	800 mm	800 mm	1000 mm	1000 kg		